

آدرس: تهران، خیابان ونک، کوچه ارم، پلاک۱ ، واحد ۶ ، کدپستی ۱۹۹۴۷۳۳۱۳۱ تلفن: ۸ - ۲۷ ۸۸ ۷۹۷ ۸۸ (۲۰۱) | فکس: ۳۵ ۸۸ ۸۸ (۲۱۰)

Add: Suite 6, No.1, Eram Alley, Vanak St., Tehran-1994733131-Iran T: (+98 21) 8879 08 27-8 | F: (+98 21) 8888 07 35 | info@plastickarco.com

## **Technical Data Sheet**

## **Stretch Film – Hand Wrap**

Test	Values (listed by film thickness)						
	Reference Methods	65 gauge 16.5 micron 0.65 mil	70 gauge 17.8 micron 0.70 mil	80 gauge 20.3 micron 0.80 mil	90 gauge 22.9 micron 0.90 mil	100 gauge 25.4 micron 1.00 mil	110 gauge 27.9 micron 1.10 mil
Ultimate Tensile MD (psi)	ASTM D882	6150	6200	6200	6300	6380	6450
Ultimate Tensile TD (psi)	ASTM D882	4650	4000	4800	4900	4910	5000
Elongation MD (%)	ASTM D882	480	500	500	600	715	625
Elongation TD (%)	ASTM D882	640	650	670	735	810	750
Tear Resistance MD (grams and g/mil)	ASTM D1922	40 grams 61.5 g/mil	42 grams 60 g/mil	90 grams 113 g/mil	92 grams 102 g/mil	92 grams 92 g/mil	97 grams 88.2 g/mil
Tear Resistance TD (grams and g/mil)	ASTM D1922	474 grams 729 g/mil	530 grams 757 g/mil	350 grams 438 g/mil	320 grams 356 g/mil	337 grams 337 g/mil	350 grams 318 g/mil
Dart Drop (grams and g/mil)	ASTM D1709	50 grams 76.9 g/mil	58 grams 82.9 g/mil	61 grams 76.3 g/mil	65 grams 72.2 g/mil	73 grams 73 g/mil	75 grams 68.2 g/mil
Pre-stretch (% at break)	IPG/Highlight	220	265	275	285	300	325

While we believe them to be reliable, the statements and information herein are only for general and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages any kind. Including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.